

Geogrid/nonwoven composite

Combigrid® 30/30 Q1 151 GRK 3



NAUE GmbH & Co. KG
Gewerbstrasse 2
32339 Espelkamp-Fiestel, Germany

Phone: +49 5743 41-0 · Fax: +49 5743 41-240
E-Mail: info@naue.com · Internet: www.naue.com



Global Synthetics

www.globalsynthetics.com.au

Sydney 8/28 Dramzi Rd, Girraween, NSW 2145
Phone: 02 9631 0744 · Fax 02 9631 0755

Australian Company – Global Expertise

Brisbane 44 Telford St, Virginia, QLD 4014
Phone: 07 3865 7000 · Fax 07 3865 4444

info@globalsynthetics.com.au

Perth 17 Church Rd, Maddington, WA 8109
Phone: 08 9459 4300 · Fax 08 9459 4311

Product description:

Composite of a laid geogrid made of stretched, monolithic polypropylene (PP) flat bars with welded junctions and a mechanical bonded filter geotextile welded within the geogrid structure, used for the reinforcement in many fields of civil engineering including road construction, landfill and hydraulic engineering

Property	Test method*	Unit	30/30 Q1 151 GRK 3
Geogrid			30/30 Q1
Raw material	-	-	polypropylene (PP), white
Mass per unit area	EN ISO 9864	g/m ²	200
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	≥ 30 / ≥ 30
Elongation at nominal strength, md / cmd**	EN ISO 10319	%	≤ 8 / ≤ 8
Tensile strength at 2% elongation, md / cmd**	EN ISO 10319	kN/m	12 / 12
Tensile strength at 5% elongation, md / cmd**	EN ISO 10319	kN/m	24 / 24
Aperture size, md x cmd**	-	mm x mm	approx. 32 x 32
Production specific elongation	-	%	0
Geotextile			151 GRK 3
Raw material	-	-	polypropylene (PP), white
Mass per unit area	EN ISO 9864	g/m ²	≥ 150
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	7.5 / 11.0
Elongation at max. tensile strength, md / cmd**	EN ISO 10319	%	40 / 30
Puncture force	EN ISO 12236	N	1,670
Displacement at static puncture strength	EN ISO 12236	mm	30
Detector tested	-	-	yes
Roll dimensions, width x length	-	m x m	4.75 x 100

*based on, **md = machine direction, cmd = cross machine direction

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.