



PROPAVE PAVING FABRIC

TYPICAL PROPERTIES

| CHARACTERISTIC | TEST STANDARD | UNITS | PROPAVE PP1 | PROPAVE PP2 |
|-------------------------------------|---------------|------------------|-------------|-------------|
| TENSILE PROPERTIES | | | | |
| Wide Strip Tensile Strength | AS 3706.2 | kN/m | ≥ 7.0 | ≥ 10.0 |
| Wide Strip Elongation | AS 3706.2 | % | 40 - 70 | 40 - 70 |
| G rating | (QMR) | - | ≥ 950 | ≥ 1100 |
| BITUMEN RETENTION PROPERTIES | | | | |
| Bitumen Retention (Class 170) | ASTM D6140 | l/m ² | ≥ 0.9 | ≥ 1.1 |
| PHYSICAL PROPERTIES | | | | |
| Polymer | | - | Polyester | Polyester |
| Melt Point | | Deg C | > 250 | > 250 |
| Mass | AS 3706.1 | g/m ² | 140 | 180 |
| Thickness | AS 3706.1 | mm | ≥ 0.8 | ≥ 1.2 |
| Standard Roll Size* | | m | 4 x 300 | 4 x 200 |
| Nominal Roll Weight | | kg | 170 | 150 |

*Roll widths and lengths may be varied to suit the paving application. Typically roll widths between 2m and 4.5m may be supplied. Product is supplied on plastic inner cores to minimise damage.

DISTRIBUTORS OF :

- Geotextiles**
- Geogrids**
- Dewatering Tubes**
- Subsoil Drainage**
- Wick Drains**
- Erosion Control**
- Gabions & Rock Mattresses**
- Industrial Fabrics**
- Lining Systems**

ProPave is a registered trademark of Global Synthetics Pty Ltd.

ProPave geotextiles are manufactured to ISO 9001 quality assurance procedures. ProPave Geotextiles are made from polyester filaments that are highly durable and resistant to all natural occurring soil acids and alkalis. Polyester geotextiles are unaffected by bacteria and fungi. Properties of ProPave textiles are typical values and correspond to average values derived from in house and independent laboratory testing.

DISCLAIMER : All information provided in this publication is correct to the best knowledge of the company and is given out in good faith. The information presented herein is intended only as a general guide to the use of such products and no liability is accepted by Global Synthetics Pty Ltd and Global Synthetics QLD Pty Ltd for any loss or damage however arising, which results either directly or indirectly from the use of such information. Global Synthetics Pty Ltd and Global Synthetics QLD Pty Ltd have a policy of continuous development so information and product specifications may change without notice.

SEP.10

