

ProLiner® LLDPE DOUBLE SIDED TEXTURED GEOMEMBRANE

LINING SYSTEMS

DESCRIPTION

LLDPE textured/textured geomembranes have a generalised use as high friction lining materials for leachate pads, channels, dams & containment structures. LLDPE is a polymer with very short & uniform branches which make its melt temperature, tensile strength & cracking resistance superior to LDPE. ProLiner LLDPE is a non polar, semicrystalline thermoplastic with good mechanical properties, high chemical stability & electrical insulation. ProLiner LLDPE does not absorb humidity, is odourless & is physically inert. ProLiner LLDPE geomembranes are manufactured with resins which are specially formulated & certified.

LLDPE textured/textured geomembranes have a density from 0.928 - 0.939 g/cm³. ProLiner LLDPE textured/textured geomembranes have low permeability, high stress resistance & flexibility, high break elongation & good chemical & UV resistance (2-3% carbon black). ProLiner LLDPE is textured on both sides for improved frictional resistance of the liner on inclined slopes and for cover materials above the liner.

Available in rolls of up to 125m long x 8m wide for 1mm thick product. All product is available in 8m width and roll length decreases with thickness increase.

PROPERTIES	UNIT	TEST METHOD	STANDARD 1.00MM	STANDARD 1.50MM	STANDARD 2.00MM	STANDARD 2.50MM
Thickness Average nom.(-5%)	mm	ASTM D 5994	0.95	1.425	1.9	2.375
Thickness Min (-15%)	mm	ASTM D 5994	0.85	1.275	1.70	2.125
Asperity Height (min avg.)	mm	ASTM D 7466	0.25	0.25	0.25	0.25
Density (max)	g/cm ³	ASTM D 792	0.939	0.939	0.939	0.939
Tensile Properties:		ASTM D 6693				
<i>Break Strength</i>	kN/m	Type IV	11	16	21	26
<i>Break Elongation</i>	%		300	300	300	300
2% Modulus (max)	N/mm	ASTM D 5323	420	630	840	1050
Tear Resistance	N	ASTM D 1004	100	153	204	255
Puncture Resistance	N	ASTM D 4833	220	330	440	550
Axi-Symmetric Break Resistance Strain (min)	%	ASTM D 5617	30	30	30	30
Carbon Black Content	%	ASTM D 1603	2.0-3.0	2.0-3.0	2.0-3.0	2.0-3.0
Carbon Black Dispersion	Cat	ASTM D 5596	1-2	1-2	1-2	1-2
Oxidative Induction Time (OIT)	min	ASTM D 3895	100	100	100	100
Oven Ageing at 85°C <i>Standard OIT (90 days)</i>	%	ASTM D 5721 ASTM D 3895	35	35	35	35
UV Resistance <i>High Pressure OIT (1600 hours)</i>	%	GM 11 ASTM D 5885	35	35	35	35



DISTRIBUTORS OF :

- Geotextiles**
- Geogrids**
- Dewatering Tubes**
- Subsoil Drainage**
- Wick Drains**
- Erosion Control**
- Gabions & Rock Mattresses**
- Industrial Fabrics**
- Lining Systems**



Global Synthetics
AUSTRALIAN COMPANY - GLOBAL EXPERTISE

ProLiner is a registered trademark of Global Synthetics Pty Ltd.
ProLiner is manufactured to ISO9001, quality assurance procedure. Properties of ProLiner are minimum typical roll values unless otherwise noted.
(GM) refers to the Geosynthetic Research Institute GRI-USA.

DISCLAIMER : All information provided in this publication is correct to the best knowledge of the company and is given out in good faith. The information presented herein is intended only as a general guide to the use of such products and no liability is accepted by Global Synthetics Pty Ltd and Global Synthetics QLD Pty Ltd for any loss or damage however arising, which results either directly or indirectly from the use of such information. Global Synthetics Pty Ltd and Global Synthetics QLD Pty Ltd have a policy of continuous development so information and product specifications may change without notice. SEP.10

SYDNEY

P: (02) 9631 0744

F: (02) 9631 0755

E: info@globalsynthetics.com.au

BRISBANE

P: (07) 3865 7000

F: (07) 3865 4444

PERTH

P: (08) 9459 4300

F: (08) 9459 4311

www.globalsynthetics.com.au